

APPLICATION DATA SHEET

BLACKFAST 182 IRON/STEEL BLACKING CREAM

USE: As supplied

APPLICATION: Ensure surface is physically and chemically clean by removing all traces of oil and grease (use Blackfast 716 cold alkaline degreaser) and all traces of rust and scale (use Blackfast 513 acid pickle) followed by rinsing in water.

Apply Blackfast 182 cream direct to a wet surface and leave for 5 - 10 minutes. Wipe with a damp cloth or wash with water. Repeat the application if blacking is incomplete or uneven. Immerse in a dewatering oil (use Blackfast 833) to ensure protection against corrosion.

If cream begins to separate on storage, stir and allow to reset before use

PRODUCT SAFETY

DATA SHEET: A safety data sheet is available.

Blackfast 182 is part of the Blackfast range of products for the treatment of iron, steel and aluminium at low temperatures.

Blackfast Chemicals continues to improve the quality and performance of its range of products and reserves the right to modify product formulations without prior notice.

AUGUST 2015